

RSFR-H

3:1 Yellow/Green

**RSFR-H 3:1 Yellow/Green - Heat shrinkable polyolefin tubing**UL approved
UL category YDPU2/8
File E203950

Item description:	Flame Retardant – Heat Shrinkable Tube
Item Code:	RSFR-H (Yellow/Green) shrinking ratio 3:1
UL File:	E203950–Cat. UL YDPU2/8 (Tubing, Extruded Insulation – Component) VW-1 600Volt

This specification defines technical requirement, testing method, testing rules and packing of heat shrinkable tubes.

Applications

RSFR-H 3:1 yellow/green heat shrinkable tubing is used as connection, protection, identification... of electrical cables. Also used as electrical insulation, mechanical protection in general; as a protection of metallic rods, tubes, antenna...

Standard

Standard for Extruded Electrical Tubing UL224

Description

RSFR-H 3:1 yellow/green tube is extruded, radiate to make it cross linked, then expanded and cooled at the required size.

Technical requirements:

Temperature ranges: -55°C +125°C
Shrinking ratio: 3:1
Shrinking temperature: 125°C
Longitudinal shrinking: ≤ 8% (±5%)

Colors: Yellow/Green



Via Abitazione, 5/1 Loc. Monteveglio
40050 Valsamoggia (BO) Italy
Tel. 0039 051 832485 Fax 051 832601
e-mail: info@isolcavi.it www.isolcavi.com



Technical specifications		Testing method	Requirement
Specification	Tensile strenght /MPa	ASTM D2671	≥10.4
	Elongation %	ASTM D2671	≥200
	Tensile strenght after aging /MPa	UL224 158°Cx168hr	≥7.3
	Elongation after aging %	UL224 158°Cx168hr	≥100
	Dielectric strenght KV/mm	IEC 243	≥15
	Volume resistance Ω cm	IEC 93	≥1x10 ¹⁴
	Flammability	UL224	VW-1

Dimensional values			
As supplied mm.	After recovery mm.		Packing mt.
Diam.mm.	Diam.mm.	Thickness mm.	
3/1	≤ 1.0	0.55 ± 0.15	200
4.5/1.5	≤ 1.5	0.60 ± 0.15	100
6/2	≤ 2.0	0.65 ± 0.15	100
9/3	≤ 3.0	0.75 ± 0.15	50
12/4	≤ 4.0	0.75 ± 0.20	50
19/6	≤ 6.0	0.85 ± 0.20	50
24/8	≤ 8.0	1.00 ± 0.20	50
39/13	≤ 13.0	1.50 ± 0.20	50

It must be stored in a dry place, inside plastic bags, away from direct sunlight, weathering, chemical materials, direct heat sources or fire. Storage time is 12 months.

The values given above are believed to be accurate and given as a matter of information only. As usage conditions are beyond our control we suggest the customer to confirm values and product compatibility prior to its use. We don't guarantee nor accept any responsibility for any particular usage.



Via Abitazione, 5/1 Loc. Monteveglio
40050 Valsamoggia (BO) Italy
Tel. 0039 051 832485 Fax 051 832601
e-mail: info@isolcavi.it www.isolcavi.com

